



DATA SHEET

SYNTHETIC WATERPROOF GREEN GREASE

PRODUCT

**Waterproof multi-
purpose EP grease.
Highly fortified with
synthetic polymers**

Color – Green



“The Best Grease Money Can Buy”

Omni Lubricants
P.O. Box 51080
Denton, TX 76206-1080
www.omnilubricants.com
Phone: 972.221.9500
FAX: 972.221.9868
sales@omnilubricants.com

GENERAL APPLICATIONS:

- Cars, Trucks, Boats, Boat Trailer wheel bearings, 4-Wheelers, Tractors, Heavy Equipment, Farm Equipment
- Power and paper plants
- Machinery exposed to wet conditions, steam, sprays, or even operating underwater!
- Suitable for bearings, seals, bushings and open gears
- Chemical plants, food plants, breweries
- General-purpose lubrications
- Marine lubrication
- Mining and heavy-duty equipment
- Off shore drilling rigs
- Flexible geared couplings
- Transport vehicle.

BENEFITS

- Waterproof—protects bearings, seals and open gears against costly wear.
- Chemical Resistant—minimizes corrosive wear in a wide variety of chemical environments.
- Extends lube cycles—grease will not wash out.
- Tenacious synthetic polymers resist high impact, shock loads and washout.
- Reduces friction, wear and down time—As down time decreases, production goes up.
- Unsurpassed sealing qualities, drastically reduces contamination of surrounding fluids and operating parts.
- Special EP compounding helps to prevent wear under heavy-duty conditions.

SPECIFICATIONS: WATERPROOF GREEN GREASE

Thickener	Mixed Complex
NLGI	2
Unworked Penetration 25°C (77°F) D217	280/310
Worked Penetration 25°C (77°F) D217	285/315
Dropping Point 290°C (554°F) D566	554°F
Water Washout Test D1264	PASS
Rust Test D1743	PASS #1
Corrosion Test D130	PASS
Timken OK Load lbs D2509	80
Four Ball EP Test Weld Load kg D2956	800kg+
Four Ball Wear Scar mm D2266	0.17mm
Base Fluid Viscosity CST 40°C (104°F)	920
Base Fluid Viscosity CST 100°C (212°F)	58
Viscosity Index	120
Lubricating Solids	Present
EP Additives	Present
Synthetic Polymers	Present
Operating Temperature Range	-25°F to 500°F

Notes: 1. Subject to the usual manufacturing tolerances
2. Test methods are ASTM unless otherwise specified